

Biobase Sweden AB Ostmästargränd 8C, SE-120 40 Årsta, SWEDEN www.bioba.se info@bioba.se +46-(0)8-520 275 90



BIO-FOMO®2

General purpose form oil



DESCRIPTION

BIO-FOMO® 2 is a general-purpose product for most types of concrete work and form materials. The product is recommended for use down to -5°C. The product is odorless and gives an excellent surface finish without discolorations.

TECHNICAL DATA			
Lowest temperature for use		-5 °C	
Viscosity at 40°C		13 mm²/s	
Flash point		>100 °C	
Biocarbon content ¹		97 %	
German water risk class		WGK 1	
Carbon footprint ²	(kg CO ₂ -eq/kg)	1,57	
Uptake		-4,69	
VOC ³		0 %	

Readily Biodegradable⁴

PRODUCT COMPOSITION

Developed and manufactured by Biobase Sweden AB from renewable raw materials. Bio-based product according to EN 16575:2014.

TECHNICAL DATA SHEET

BIO-FOMO® 2 is a bio-based form oil of medium viscosity which has been developed for the future to meet the demands on environmental friendliness and independence of fossil resources.

DIRECTIONS FOR USE

FORM MATERIAL

\checkmark	Wood	The product is applied in a thin,	
	Steel	even layer with a low pressure	
Ľ	Steel	compressed air sprayer or a paint	
\checkmark	Plastic	roller. Mop up surplus oil with a	
	Polystyrene	rag to avoid pore formation. 1 Liter	
	, ,	covers 30-50 m ²	

ENVIRONMENT & SAFETY

- REACH-compliant and unclassified according to CLP
- Not classified as dangerous goods
- Bio-based & Biodegradable

Registered in the Swedish BASTAsystem and recommended product at Byggvarubedömningen.



See the product safety data sheet for full information on safety and handling.

PACKAGING

Our packaging (5, 20, 25, 208, 1000 liters) is made of

recycled plastic (PE). The product can also be delivered on site through the BASECAMP[®] filling station.

The product can be stored for up to three years in unopened packaging. Do not store in direct sunlight. Avoid storage at high temperatures.



¹ASTM D6866 ²Carbon footprint for production of the liquid (excluding packaging) at delivery (Cradle-to-Gate) based on third party verified LCA acc. to ISO 14040/14044. ³Volatile organic compounds in % by weight. ⁴All components degrade to over 60% in 28 days in OECD 301B.

CN-number

3403 99 00 00